

NOCHAR'S FIRE PREVENTER TEST SUMMARY

APPLICATION

LABORATORY	TYPE	METHOD	TEST#	MATERIAL	RESULTS
H.P.M.A	ASTM E-84	SPRAY ON	T-6769	SPRUCE 2" X 4"	CLASS B
H.P.M.A.	ASTM E-84	SPRAY ON	T-6806	3/8 LAUAN BOARD	CLASS B
H.P.M.A	ASTM E-84	SPRAY ON	T-6767	SOUTHERN PINE PLYWOOD	CLASS C
H.P.M.A.	ASTM-E84	SPRAY ON	T-6805	¾ " RED OAK	CLASS C
H.P.M.A.	ASTM E-84	SPRAY ON	T-7259	20 LB. COMPUTER PAPER	CLASS A
H.P.M.A.	ASTM E-84	SPRAY ON	T-7187	½ " PINE SHAKES	CLASS B
H.P.M.A.	ASTM E-84	CHAMBER TREAT	T-7466	15/32 " PLYWOOD	CLASS A
H.P.M.A.	ASTM E-84	CHAMBER TREAT	T-7473	SPRUCE 2" X 4"	CLASS A
U.S. TESTING	ASTM E-84	SPRAY ON	178375	¾" DOUGLAS FIR	CLASS B

100% COTTON CLOTH PASSED ULC-S1098-M1980 STANDARD

PAPER CHIP BOARD PASSED D.O.T. 302 STANDARD

TOXICITY TESTS

LABORATORY: NORTHVIEW PACIFIC LABS.

TYPE OF TEST: ORAL, DERMAL, EYE TOXICITY

TEST REPORT # X5J56G

RESULTS: PASSED EPA GUIDELINES, FIFRA GUIDELINES, PESTICIDE ASSESSMENT GUIDELINES SEC. F

HAZARD EVALUATION: HUMAN AND DOMESTIC ANIMALS, 40 CFR; PART 158, OCTOBER 1982

ACQUATIC TOXICITY TEST; PASSED LC 50 WITH > 700 MG/L RATING (BIOMONITORING LABS.)